

Material : POLYGLYKOL 8000 PG
Material number :
Batch number :
Customer :

Date printed: 07/09/2014

Page: 2 / 2 C of A

Characteristics/
Method

	Specification	Result UOM
Appearance: Molten PAE-01		Accepted
Color (Hazen 25% Active in H2O) PAE-05	<= 50	3 [-]
pH (5% Aqueous Solution) PAE-02	5.5 - 7.5	7.0 [-]
% Water PAE-04	<= 0.75	0.07 %
Viscosity @ 98.9 C PAE16	470.0 - 900.0	882.0 cSt
Molecular Weight PAE-06	7000 - 9000	8373 g/mol

Date of Production: 07/09/2014

Date of Analysis : 07/09/2014

THE ABOVE DATA WAS OBTAINED USING THE TEST INDICATED AND IS SUBJECT TO THE DEVIATION INHERENT IN THE TEST METHOD. RESULTS MAY VARY UNDER OTHER TEST METHODS OR CONDITIONS.

The report is electronically generated and does not require a signature.